

## Fast-Setting Two-Component Polyurea Control-Joint Filler

### Description

**FastPatch**® CJF-CC is a two-component, self-leveling, 100% solids hybrid polyurea, control-joint filler designed to protect joints in industrial concrete floors subject to hard wheels and heavy loads. FastPatch® CJF-CC provides excellent resistance to spalling, abrasion, chemical attack, and corrosion. It is also ideal for filling random cracks.

### Applications

- Control joints in concrete – interior or exterior
- Retail and warehouse floors
- Random crack filling

### Advantages

- Rapid gel time – reduces facility down time
- Rapid return to service – trim in as little as an hour
- No VOCs – very low odor
- Low viscosity - flows into place easily
- High abrasion resistance – approved for hard-wheel traffic
- Compliant with USDA rules for Incidental Food Contact - can be used in meat and poultry plants
- Made in America

### Typical Properties

Description	Result	Method
VOC	0 lbs/gal (0 g/L)	ASTM D2369
Viscosity	1700 cps iso, 1700 cps resin	ASTM D4878
Tensile strength	1400 psi (9.6 MPa)	ASTM D412
Elongation	100%	ASTM D412
Hardness	90 Shore A	ASTM D2240

### Processing Parameters

Service temperature	-40 to 350° F (-40 to 177° C)
Gel time	60 seconds
Trim time	1-12 hours
Return to service	1-3 hours

### Color

Gray

### Packaging

600-mL cartridge (case of 12)  
 1500-mL cartridge (case of 4)  
 5-Gallon (19 L) pails  
 50-Gallon (190L) drums

### Shelf life

1 year at recommended storage conditions.

### Storage

Store and ship this product in a clean, dry, low-humidity, shaded or covered environment at 60 to 90° F (15 to 32° C).

## ■ Chemical Resistance

Type	Δ weight	Δ volume
H <sub>2</sub> O	+	+
10% NaCl	+	+
10% NaOH	+	++
10% CaCl <sub>2</sub>	+	++
5% H <sub>2</sub> SO <sub>4</sub>	+	++
0.3% NaClO (bleach solution)	+	+
ASTM Oil #1	++	+
ASTM Oil #2	++	++
ASTM Oil #3	+	+
Jet Fuel A	+	+

+ Good  
++ Excellent

FastPatch® CJF-CC is resistant to a wide variety of chemicals at varying concentrations. Please contact your FastPatch® representative for the chemical resistance specific to your application.

## ■ Estimated coverage

Yield, linear feet (meters) per gallon of material

Joint width inch (cm)	Joint depth inch (cm)		
	1.0" (2.5 cm)	1.5" (3.8 cm)	2" (5.1 cm)
0.25" (0.64 cm)	76" (23 cm)	51" (15 cm)	38" (12 cm)
0.375" (0.95 cm)	51" (15 cm)	34" (10 cm)	25" (7.6 cm)
0.5" (1.3 cm)	38" (12 cm)	25" (7.6 cm)	19" (5.8 cm)

## ■ Health & Safety

Before handling, you should become familiar with Safety Data Sheet regarding the risks and safe use of this product. To obtain an SDS please email [PolyQuik@wilvaco.com](mailto:PolyQuik@wilvaco.com)

## ■ Disclaimer of Warranty

Test results are to be considered as representative of current production and should not be treated as specifications. While all the information presented in this document is believed to be reliable and to represent the best available data on these products, no guarantee, warranty, or representation is made, intended, or implied as to the correctness or sufficiency of any information, or as to the suitability of any chemical compounds for any particular use, or that any chemical compounds or use thereof are not subject to a claim by a third party for infringement of any patent or other intellectual property right. Each user should conduct a sufficient investigation to establish the suitability of any product for its intended use. Proper application is the responsibility of the user. As with any product, the use of this product in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability. Testing is the requirement of both engineers and contractors alike. WVCO does not warrant the application under any or all circumstances.